


High performance tap (sintered steel) for cast iron.



- Especially for cast irons
- TiCN coating

Machine



Application



K- Ferrous Cast iron with Short Chips

Features



Properties and benefits

- + TiCN coating : Thickness 2/4µm, hardness 3500 HV, coefficient of friction 0,15, resistance to heat (400°C). High toughness while maintaining a very high hardness. Reduced coefficient of friction. Increased tool life. Special steels.



Code	EAN	Thread	Ø	Pitch	Norm	Drill	L	I	I4	I5	QTY	PCB
960CT1100300050	8420609526572	M	3	0,5	DIN 371	2,50	56	10	2-3	2,70	1	1
960CT1100400070	8420609526589	M	4	0,7	DIN 371	3,30	63	12	2-3	3,40	1	1
960CT1100500080	8420609526596	M	5	0,8	DIN 371	4,20	70	14	2-3	4,90	1	1
960CT1100600100	8420609526602	M	6	1	DIN 371	5,00	80	16	2-3	4,90	1	1
960CT1100800125	8420609526626	M	8	1,25	DIN 371	6,75	90	18	2-3	6,20	1	1
960CT1101000150	8420609526633	M	10	1,5	DIN 371	8,50	100	20	2-3	8,00	1	1
960CT1101200175	8420609526640	M	12	1,75	DIN 376	10,25	110	22	2-3	7,00	1	1
960CT1101400200	8420609526657	M	14	2	DIN 376	12,00	110	25	2-3	9,00	1	1
960CT1101600200	8420609526664	M	16	2	DIN 376	14,00	110	28	2-3	9,00	1	1
960CT1100800100	8420609526619	MF	8	1	DIN 371	7,00	90	18	2-3	6,20	1	1
960CT1101000100	8420609596247	MF	10	1	DIN 371	9,00	90	18	2-3	8,00	1	1
960CT1101200150	8420609596254	MF	12	1,5	DIN 374	10,50	100	22	2-3	7,00	1	1
960CT1101400150	8420609596261	MF	14	1,5	DIN 374	12,50	100	22	2-3	9,00	1	1