

Tap for steels. STEAM treatment avoids cold gluing and reduces the friction coefficient.




- Threading of standard Steels
- 5% cobalt HSS
- STEAM treatment

### Machine



### Application



### Features



### Properties and benefits

- + 5% cobalt high-speed steel: HSS substrate enriched with 5% cobalt. Improved heat retention (strength, cutting sharpness) ➡ For general use in metals up to 1200 N/mm<sup>2</sup>.
- + STEAM treatment : Steam oxidation treatment. ➡ Avoids cold bonding. Reduced coefficient of friction in steels.



Code	EAN	Thread	Ø	Pitch	Norm	Drill	L	I	I4	I5	QTY	PCB
970401100300050	8420609364952	M	3	0,5	NFE 66101		280	12,5			1	1
970401100400070	8420609364983	M	4	0,7	NFE 66101		280	18			1	1
970401100500080	8420609365027	M	5	0,8	NFE 66101		280	20			1	1
970401100600100	8420609365058	M	6	1	NFE 66101		280	25			1	1
970401100700100	8420609365072	M	7	1	NFE 66101		280	25			1	1
970401100800125	8420609365102	M	8	1,25	NFE 66101		280	32			1	1
970401101000150	8420609365171	M	10	1,5	NFE 66101		280	38			1	1
970401101200175	8420609365249	M	12	1,75	NFE 66101		420	44			1	1
970401101400200	8420609365317	M	14	2	NFE 66101		420	50			1	1
970401101600200	8420609365386	M	16	2	NFE 66101		520	50			1	1
970401101800250	8420609365423	M	18	2,5	NFE 66101		520	63			1	1
970401102000250	8420609365461	M	20	2,5	NFE 66101		520	63			1	1
970401102400300	8420609365553	M	24	3	NFE 66101		520	75			1	1
970401100600075	8420609365041	MF	6	0,75	NFE 66101		280	25			1	1
970401100800100	8420609365096	MF	8	1	NFE 66101		280	32			1	1
970401101000100	8420609365157	MF	10	1	NFE 66101		280	38			1	1
970401101200125	8420609365225	MF	12	1,25	NFE 66101		420	38			1	1
970401101200150	8420609365232	MF	12	1,5	NFE 66101		420	44			1	1
970401101400150	8420609365300	MF	14	1,5	NFE 66101		420	50			1	1